



MÁRMOL VERDE ALPI

TECHNICAL DATA SHEET

Commercial name: Spider Green

Technical Data and Mechanical properties:

Apparent density	2610 kg/m ³
Open porosity	1.4% vol.
Flexural strength	9 MPa
Compressive strength	398 kg/cm ²
Water absorption	0.48 % wt.
Abrasion resistance	1.1cm (groove depth)
After Freezing	2777 kg/cm ²
Ultimate Tensile Strengt	261 kg/cm ²
Hardness (Moh's Scale)	4.8

(*) This information is based on our present knowledge out of laboratory tests and other information sources..

However, this shall not constitute a guarantee for any specific batch of stone, and shall not establish a legally valid contractual relationship.